

Strong Modul 766 BT


Manufacturing process	Needlefelt		ISO 2424					
Type of surface	Flecked							
Surface aspect	Coarse Fibred		ISO 2424					
Width	50*50 cm		EN 984					
Backing	BT		ISO 2424					
Fibre composition	70% PP / 30% dorix® PA							
Total fibre weight of use surface	450 gr/m ²							
Total weight	4140 gr/m ²	+/- 15%	ISO 8543					
Total height	6,5 mm	+15% / -10%	ISO 1765					
Overall use class	Commercial 33, Areas with heavy use		EN ISO 10874					
Luxury class	LC1		EN 1307					
Castor chair suitability	Yes, permanent use		EN 985					
Colour fastness to light	≥ 5		ISO 105-B02					
Colour fastness to rubbing, wet and dry	≥ 4		ISO 105-X12					
Colour fastness to water	≥ 4		ISO 105-E01					
Electrostatic charging	< 2kV		ISO 6356					
Impact sound protection ΔLW	20 dB		ISO 10140					
Acoustical sound absorption αS	Hz	125	250	500	1000	2000	4000	ISO 354
	αW	0,00	0,03	0,06	0,13	0,30	0,31	
Evaluated sound absorptions grade αW	15							ISO 11654
Thermal resistance	0,07 m ² .K/W							ISO 8302
Slip resistance	DS (> 0,30)							EN 13893
Flammability	Bfl,s1							EN 13501-1
Prodis-ID (GuT)	803DB22A							www.pro-dis.info
TÜV PROFICERT product	Certificate number: 70 710 5617-5							

Floorsymbols



Certificates

EN 14041




Reaction to fire:
Bfl,s1


Slip resistance:
DS

DOP:
1061#Z03BT00
Textile Floorcovering
EN1307









Mitglied der
DGNB
Deutsche Gesellschaft für Nachhaltiges Bauen
German Sustainable Building Council



tested for: emissions
harmful substances
PREMIUM