

Strong Modul 966

| | | | | | | | | | | | | | | | | | |
|--|--|-------------|--------------|------|------|------|------------------|------|----|------|------|------|------|------|------|--|---------|
| Fabricagemethode | Needlefelt | | ISO 2424 | | | | | | | | | | | | | | |
| Vezeloptiek | Flecked | | | | | | | | | | | | | | | | |
| Poolbeeld | Coarse Fibred | | ISO 2424 | | | | | | | | | | | | | | |
| Breedte | 50*50 cm | | EN 984 | | | | | | | | | | | | | | |
| Rugafwerking | BT | | ISO 2424 | | | | | | | | | | | | | | |
| Vezelmateriaal | 70% doric® PA / 20% PES / 10% PP | | | | | | | | | | | | | | | | |
| Vezelgewicht | 500 gr/m ² | | | | | | | | | | | | | | | | |
| Totaal gewicht | 4200 gr/m ² | +/- 15% | ISO 8543 | | | | | | | | | | | | | | |
| Basisgewicht pool | 450 gr/m ² | +/- 15% | EN 984 | | | | | | | | | | | | | | |
| Totaal hoogte | 6,5 mm | +15% / -10% | ISO 1765 | | | | | | | | | | | | | | |
| Gebruiksklasse | Commercial 33, Areas with heavy use | | EN ISO 10874 | | | | | | | | | | | | | | |
| Comfort klasse | LC1 | | EN 1307 | | | | | | | | | | | | | | |
| Zwenkwielsingeschiktheid | Yes, permanent use | | EN 985 | | | | | | | | | | | | | | |
| Kleurechtheid licht | ≥ 5 | | ISO 105-B02 | | | | | | | | | | | | | | |
| Kleurechtheid wrijven, nat en droog | ≥ 4 | | ISO 105-X12 | | | | | | | | | | | | | | |
| Kleurechtheid water | ≥ 4 | | ISO 105-E01 | | | | | | | | | | | | | | |
| Statische oplading | < 2kV | | ISO 6356 | | | | | | | | | | | | | | |
| Doorgangsweerstand | ≤ 1,0x10 ⁸ Ω | | ISO 10965 | | | | | | | | | | | | | | |
| Akoestische schokdemping ΔLW | 20 dB | | ISO 10140 | | | | | | | | | | | | | | |
| Akoestische geluiddempingsgraad αS | <table border="1"> <tr> <td>Hz</td> <td>125</td> <td>250</td> <td>500</td> <td>1000</td> <td>2000</td> <td>4000</td> </tr> <tr> <td>αW</td> <td>0.00</td> <td>0.03</td> <td>0.06</td> <td>0.13</td> <td>0.30</td> <td>0.31</td> </tr> </table> | Hz | 125 | 250 | 500 | 1000 | 2000 | 4000 | αW | 0.00 | 0.03 | 0.06 | 0.13 | 0.30 | 0.31 | | ISO 354 |
| Hz | 125 | 250 | 500 | 1000 | 2000 | 4000 | | | | | | | | | | | |
| αW | 0.00 | 0.03 | 0.06 | 0.13 | 0.30 | 0.31 | | | | | | | | | | | |
| Akoestische geluiddempingsgraad αW | 0.15 | | | | | | ISO 11654 | | | | | | | | | | |
| Warmtedoorlaatbaarheid | 0.08 m ² .K/W | | | | | | ISO 8302 | | | | | | | | | | |
| Slipweerstand | DS (> 0,30) | | | | | | EN 13893 | | | | | | | | | | |
| Brandwerendheid | Bfl,s1 | | | | | | EN 13501-1 | | | | | | | | | | |
| Prodis-ID (GuT) | AEDFFFD6 | | | | | | www.pro-dis.info | | | | | | | | | | |
| TÜV PROFICERT product | Certificaatnummer: 70 710 5617-4 | | | | | | | | | | | | | | | | |

Produktinformatie tapijtsymbolen



Certificaten

